

PRODUCT SPECIFICATION SHEET

Guaraply C+/C 18mm

September 2007

| | | | |
|-----------------------|--|--|------------------------|
| Description: | Plywood panels with one side repaired & sanded |  <p>THIS PRODUCT MEETS THE BOND PERFORMANCE REQUIREMENTS FOR EXPOSURE 1 PLYWOOD</p> <p>GuaraPly Mill 252</p> | |
| Producer: | Industria de Compensados Guararapes Ltda. Rua Alcina Santos Araújo, 411 85555-000 Palmas, PR, Brazil | | |
| Contact: | Mr. José Carlos Januário Export Manager Phone: +55 (46) 3263 8300 Fax: +55 (46) 3263 8310 E-mail: januario@guararapes.com.br www.guararapes.com.br | | |
| Qualification: | PS 1-07 Meets the Exposure 1 glue lines requirements. | | |
| Certified by: | TECO 9015 Newcastle Drive Shreveport, Louisiana 71129-5123 USA | | |
| Contact: | Mr Richard Bower, Plywood Certification Supervisor TECO 2902 Terra Court Sun Prairie, Wisconsin 53590-9814 USA Phone: (608) 837-2790 E-mail: dick.bower@tecotested.com | | |
| Intended use: | For general purposes where the structural performance is not a key requirement. | | |
| Size: | Nominal: 8' x 4' (48" x 96") | Tolerances: +0 / -1/8" | |
| Thickness: | Nominal: 23/32" | Actual Minimum: 0.687" | Actual Maximum: 0.750" |
| Plies-Layers: | 7/7 | | |
| Faces: | Repaired knotholes up to 2-1/2". Knots and occasional knotholes up to 3". Repaired splits up to 1" measured at 8" of panel ends. | | |
| Backs: | Knotholes up to 2-1/2". Knots and occasional knotholes up to 3". Splits up to 1" measured at 8" of panel ends. | | |
| Inner Plies: | Knotholes up to 3". Laps up to 1/2". Gaps up to 1" at 8" from panel edges. | | |
| Species: | Slash Pine (pinus elliottii) and Loblolly Pine (pinus taeda) | | |
| Bond Quality: | Exposure 1 durability. Fully exterior phenolic resins are used to make the panels suitable for temporary exposure to weather due to construction delays or high humidity. | | |
| Packaging: | Units with 50 panels, with 5 steel straps (or more) and over 3 wooded skids. | | |